


SiSiB[®] PC5460

- 1 -

Tetra Butyl Glycol Silicate



Typical Physical Properties

Chemical Name:	Tetrakis(2-butoxyethyl)orthosilicate
Synonym:	Tetrakis(butoxyethoxy)silane
Empirical Formula	C ₂₄ H ₅₂ O ₈ Si
Molecular Weight	496.75
Color and Appearance	Colorless transparent liquid
Density _{25/25°C}	0.970
Boiling Point	205°C [1.3mmHg]
Refractive Index	N.A. [20°C]
Flash Point:	92°C
CAS No.:	18765-38-3
EINECS No.:	242-560-0
Purity	Min 98.0%

Application

Modify surface of silica to obtain hydrophobic property.

Used as crosslinkers for room temperature vulcanizing silicone sealant.

Packing

190Kg PE Drum

Shelf Life

Keep in tightly closed container. Store at cool and dry place. Shelf life is Min.12 months.